

# TREMCO®

# Tremsil® 200

## General Construction Grade Silicone Sealant

### Product Description:

Tremsil 200 is a one-part, acetoxy silicone sealant. Tremsil 200 cures to a flexible rubber when exposed to moisture present in the air.

### Basic Uses:

Tremco Tremsil 200 produces a weathertight seal to glass, metal, porcelain, ceramic and most painted surfaces. White and Clear colors can contain a fungicide making the sealant suitable for use in bathrooms, spas and similar applications where joints need protection against fungi and bacteria.

### Limitations:

- Do not apply over damp or contaminated surfaces.
- Use with adequate ventilation.

### Packaging:

1/12 gallon (300ml) cartridges.

### Standard Colors:

Aluminum, Anodized Aluminum, Black, Clear, Dark Bronze, Gray, Ivory, and White.

### APPLICABLE STANDARDS:

Conforms to ASTM C920 Type S, Grade NS, use NT, G, A, and O and CAN/CGSB-19.13-M87 and U.S. Federal Specification TT-S-00230, Class A, and U.S. Federal Specification TT-S-001543A Class A.

### INSTALLATION

#### Joint Design:

May be used in any joint designed in accordance with accepted architectural/engineering practices. Joint width should be 4 times anticipated movement, but not less than 1/4 inch (6.4mm) wide.

### Joint Dimensions:

For joints 1/4 inch (6.4mm) to 1/2 inch (12.7mm) wide, the width to depth ratio should be equal. Joints 1/2 inch (12.7mm) wide or greater should have a depth of 1/2 inch (12.7mm). Minimum joint size 1/4 inch by 1/4 inch (6.4mm by 6.4mm).

### Surface Preparation:

For good adhesion, the joint interface must be sound, clean and dry. Depending on the substrates, the joint surface may require a thorough wire brushing, grinding, sand-blasting, solvent washing and/or primer.

### Tooling & Cleaning:

Tooling is recommended immediate-

ly after application to ensure firm, intimate contact with the joint interface. Dry tooling is preferred. Cleaning can be accomplished with solvents such as IPA or MEK while sealant is in uncured state.

### Joint Backing-Bond Breaking Tape:

Closed cell polyethylene, reticulated foam and some open cell polyurethane rods may be used as joint backing to control depth of sealant bead. Where depth of joint will prevent use of joint backing, an adhesive backed polyethylene tape should be installed to prevent three side adhesion. Joint backing must be dry at time of sealant application.



**Application:**

Tremsil 200 is easy to apply with conventional caulking equipment. Fill joint completely and tool. At 75°F (23.9°C), 50% R.H. a durable skin will form within 30 minutes.

**Maintenance:**

Damaged sealant can be repaired. Consult your Tremco Distributor or Representative for repair procedures.

**Availability:**

Immediately available from your local Tremco Field Representative, Tremco Distributor or Tremco Warehouse.

**Warranty:**

Tremco warrants its Sealants to be free of defects in materials, but makes no warranty as to appearance or color. Since methods of application and on site conditions are beyond our control and can affect

performance, Tremco makes no other warranty, expressed or implied, including warranties of MERCHANTABILITY and FITNESS FOR A PARTICULAR PURPOSE, with respect to Sealants, sole obligation shall be, at its option, to replace, or to refund the purchase price of the quantity of Sealant proved to be defective and Tremco shall not be liable for any loss or damage.



For MSDS and Spec Data Sheets  
visit our website:  
[www.tremcosealants.com](http://www.tremcosealants.com)

**TREMCO**

Sealant/Weatherproofing Division

3735 Green Road • Beachwood, Ohio • 44122 • Phone: (216) 292-5000 • (800) 321-7906  
220 Wicksteed Avenue • Toronto, ON M4H 1G7 • Phone: (416) 421-3300 • (800) 363-3213



An RPM Company

PRINTED IN THE USA 0504/T200SD