

Dow Corning[®] 798 Cold & Cleanroom Silicone Sealant

FEATURES

- Neutral alkoxy cure system
- 100% silicone polymer
- Mildew resistant
- Bacteriostatic sealant
- Low modulus, high elasticity
- Low odor
- Conforms to ISO 11600-F&G-25LM
- Resistant to ozone, ultra-violet radiation and temperature extremes

Low modulus neutral silicone sealant

APPLICATIONS

- *Dow Corning*[®] 798 Cold & Cleanroom Silicone Sealant is specifically formulated for sealing areas in refrigeration units and coldrooms. It is a one-part neutral curing silicone sealant, suitable for use in either interior or exterior applications where joints are susceptible to mildew. It is a bacteriostatic sealant, better protected against the bacterial growth. *Dow Corning* 798 Silicone Sealant offers good adhesion to most porous and non-porous surfaces including masonry, tiles, aluminum, PVC-U, polyacrylate, polycarbonate, glass and glazed surfaces.

TYPICAL PROPERTIES

Specification Writers: These values are not intended for use in preparing specifications. Please contact your local Dow Corning sales office or your Global Dow Corning Connection before writing specifications on this product.

Test method*	Property	Unit	Value
	Cure system		Neutral
	Application temperature	°C	+5 to +40
		°F	+41 to +104
CTM97B	Specific gravity	g/ml	1.51
CTM364C	Extrusion rate	g/minute	200
CTM98B	Skin-over time (23°C or 73°F, 50% R.H.)	minutes	20
CTM95A	Tack-free time (23°C or 73°F, 50% R.H.)	minutes	30
CTM663A	Cure rate (23°C or 73°F, 50% R.H.)		
	1 day	mm	2.0
	3 days	mm	4.0
	2mm thickness S2 dumb-bells (ISO 37)		
CTM137A	E-Modulus 100%	MPa	0.45
CTM137A	Tensile strength	MPa	1.9
CTM137A	Elongation at break	%	700
	12x12x50mm size T.A. joint (ISO 8339/DIN2-8339)		
CTM677	E-Modulus 100%	MPa	0.35
CTM677	Tensile strength	MPa	0.75
CTM677	Elongation at break	%	380
CTM99E	Hardness (Shore A)		29
	Elastic recovery	%	>90
ISO 9047	Joint movement capability		25

* CTM: Corporate Test Method, copies of CTMs are available on request.

DIN: Deutsche Industrie Norm.

ISO: International Standardisation Organisation.

TECHNICAL SPECIFICATIONS AND STANDARDS

Conforms to SNJF Category 1,

- ISO 11600-F&G-25LM. Bacteriostatic performance has been tested to ISO 22196:2007 for MRSA, E.Coli and Salmonella and to ISO 846 for P.Aeruginosa.

HOW TO USE

Surface preparation

Ensure that surfaces to be sealed are clean, dry, sound and free from frost, release agents, old sealants and other contaminants which could impair adhesion. All non-porous surfaces should be cleaned and degreased by wiping with a suitable solvent such as *Dow Corning*® R40 Universal Cleaner, on a clean oil-and lint-free cloth before application of sealant. Porous surfaces such as concrete, brickwork, and mortar must be mechanically cleaned using a steel brush, sanding disc or other mechanical means.

Note: When using any solvent, always provide adequate ventilation. Avoid heat, sparks and open flames. Use solvent resistant gloves. Observe and follow all precautions listed on solvent container label.

Masking

Areas adjacent to the joints should be masked with tape to prevent contamination of the substrates and to ensure a neat sealant line. Masking tape should be removed immediately after tooling.

Priming

For specific advice, please refer to the *Dow Corning*® Primers' Guide or contact one of Dow Corning's Regional Service Centers for technical assistance.

Back-up materials

When back-up material is required, closed cell polyethylene backer rod is recommended. Low tack polyethylene tape should be used in joints too shallow to allow the use of backer rod. Back-up materials provide back pressure and prevent three sided adhesion that limits sealant movement capability.

Finishing

The joint should be tooled within 5 minutes of application to ensure good contact between the sealant and the substrate. Tooling of the sealant also gives a smooth, professional finish.

Clean-up

Excess sealant may be cleaned off tools and non-porous surfaces whilst in an uncured state using *Dow Corning* R40 Universal Cleaner. If sealant is misapplied to porous substrates, it should be left until just cured, and then removed by peeling, cutting or other mechanical means. Care should be taken not to damage plastic or coated surfaces.

Joint design

The sealant joint width should be designed to accommodate the movement capability of the sealant. When designing joints using

Dow Corning 798 Silicone Sealant, the minimum width should be 6mm. For joints between 6-12mm wide, a seal depth of 6mm is required. For joints above 12mm wide, a width to depth ratio of 2:1 should be used. In situations where fillet joints are needed, a minimum of 6mm sealant bite to each substrate is recommended. For joint dimensions greater than 25mm, please contact one of Dow Corning's Regional Service Centers for technical assistance.

Figure 1: Deep joint.




Figure 2: Shallow joint.





Figure 3: Fillet joint.



HANDLING PRECAUTIONS

Product safety information required for safe use is not included. Before handling, read product and safety data sheets and container labels for safe use, physical and health hazard information. The material safety data sheet is available on the Dow Corning website at dowcorning.com. You can also obtain a copy from your local Dow Corning sales representative or Distributor or by calling your local Dow Corning Global Connection.

USABLE LIFE AND STORAGE

When stored in cool, dry conditions below 30°C (86°F) in the original unopened containers, *Dow Corning 798 Silicone Sealant* has a usable life of 12 months from the date of production.

PACKAGING INFORMATION

Dow Corning 798 Silicone Sealant is supplied in 310ml cartridges, packed in boxes of 12.

LIMITATIONS

Do not use *Dow Corning 798 Silicone Sealant* on bituminous substrates, substrates based on natural rubber, chloroprene or EPDM or on building materials and flexible plastics which might bleed oils, plasticizers or solvents. Do not use *Dow Corning 798 Silicone Sealant* in a totally confined space because the sealant requires atmospheric moisture to cure.

Dow Corning 798 Silicone Sealant is not recommended for use on submerged joints or in joints where physical abuse or abrasion is likely to occur. Bleeding can occur on porous substrates such as concrete, marble, granite or other natural stones. On sensitive substrates, specific testing should be carried out. *Dow Corning 798 Silicone Sealant* is not recommended for structural glazing or insulated glazing applications.

This product is neither tested nor represented as suitable for medical or pharmaceutical uses.

HEALTH AND ENVIRONMENTAL INFORMATION

To support Customers in their product safety needs, Dow Corning has an extensive Product Stewardship organization and a team of Product Safety and Regulatory Compliance (PS&RC) specialists available in each area.

For further information, please see our website, dowcorning.com or consult your local Dow Corning representative.

LIMITED WARRANTY INFORMATION – PLEASE READ CAREFULLY

The information contained herein is offered in good faith and is believed to be accurate. However, because conditions and methods of use of our products are beyond our control, this information should not be used in substitution for customer's tests to ensure that our products are safe, effective, and fully satisfactory for the intended end use. Suggestions of use shall not be taken as inducements to infringe any patent.

Dow Corning's sole warranty is that our products will meet the sales specifications in effect at the time of shipment.

Your exclusive remedy for breach of such warranty is limited to refund of purchase price or replacement of any product shown to be other than as warranted.

DOW CORNING SPECIFICALLY DISCLAIMS ANY OTHER EXPRESS OR IMPLIED WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY.

DOW CORNING DISCLAIMS LIABILITY FOR ANY INCIDENTAL OR CONSEQUENTIAL DAMAGES.

We help you invent the future.™

dowcorning.com